



บริษัท เอดีดี เฟอร์เนส จำกัด







ADD FURNACE CO.,LTD.

44 ซอยบรมราชชนนี 70 ถนนบรมราชชนนี แขวงศาลาธรรมสพน์ เขตทวีวัฒนา กรุงเทพฯ 10170

โทร: 02-888-3472 โทร: ออกแบบ:08-08-170-170 แฟกซ์: 02-888-3258

<https://www.add-furnace.com> E-mail: sales@add-furnace.com

Honeycomb Ceramic(Infrared Burner Plate)

<p>SH2GT 46.5x133</p>		<p>Materials: Cordierite CO Discharged: <0.06 Temperature softening: 1230°C Open Porosity: 61% Air consumption: 0.13kg/h Weight: 0.05kg/sheet</p>	<p>W46.5mmxL133mmxH13mm</p>
<p>SL2WT 46.5x133</p>		<p>Materials: Cordierite CO Discharged: <0.06 Temperature softening: 1230°C Open Porosity: 61% Air consumption: 0.13kg/h Weight: 0.051kg/sheet</p>	<p>W46.5mmxL133mmxH13mm</p>
<p>SM2YT 46.5x133</p>		<p>Materials: Cordierite CO Discharged: <0.06 Temperature softening: 1230°C Open Porosity: 61% Air consumption: 0.13kg/h Weight: 0.055kg/sheet</p>	<p>W46.5mmxL133mmxH13mm</p>
<p>SMYT68 68x133</p>		<p>Materials: Cordierite CO Discharged: <0.06 Temperature softening: 1230°C Open Porosity: 61% Air consumption: 0.13kg/h Weight: 0.08kg/sheet</p>	<p>W68mmxL133mmxH13mm</p>
<p>SMYU68 68x13</p>		<p>Materials: Cordierite CO Discharged: <0.06 Temperature softening: 1230°C Open Porosity: 61% Air consumption: 0.13kg/h Weight: 0.09kg/sheet</p>	<p>W68mmxL133mmxH13mm</p>
<p>SLWT78 78x136</p>		<p>Materials: Cordierite CO Discharged: <0.06 Temperature softening: 1130°C Open Porosity: 61% Air consumption: 0.13kg/h Weight: 0.095kg/shee</p>	<p>W78mmxL136mmxH13mm</p>



บริษัท เอดีดี เฟอร์เนส จำกัด







ADD FURNACE CO.,LTD.

44 ซอยบรมราชชนนี 70 ถนนบรมราชชนนี แขวงศาลาธรรมสพน์ เขตทวีวัฒนา กรุงเทพฯ 10170

โทร: 02-888-3472 โทร: ออกแบบ:08-08-170-170 แฟกซ์: 02-888-3258

https://www.add-furnace.com E-mail: sales@add-furnace.com

Honeycomb Ceramic(Infrared Burner Plate)

SMYT78 78x136		<p>Materials: Cordierite</p> <p>CO Discharged: <0.06</p> <p>Temperature softening: 1230°C</p> <p>Open Porosity: 61%</p> <p>Air consumption: 0.13kg/h</p> <p>Weight: 0.13kg/sheet</p>	W78mmxL136mmxH13mm
SLWT 93x132		<p>Materials: Cordierite</p> <p>CO Discharged: <0.06</p> <p>Temperature softening: 1230°C</p> <p>Open Porosity: 61%</p> <p>Air consumption: 0.13kg/h</p> <p>Weight: 0.125kg/sheet</p>	W93mmxL132mmxH13mm
SMYT 93x132		<p>Materials: Cordierite</p> <p>CO Discharged: <0.06</p> <p>Temperature softening: 1230°C</p> <p>Open Porosity: 61%</p> <p>Air consumption: 0.13kg/h</p> <p>Weight: 0.25kg/sheet</p>	W93mmxL132mmxH13mm
SLWT 93x133		<p>Materials: Cordierite</p> <p>CO Discharged: <0.06</p> <p>Temperature softening: 1230°C</p> <p>Open Porosity: 61%</p> <p>Air consumption: 0.13kg/h</p> <p>Weight: 0.09kg/sheet</p>	W93mmxL133mmxH13mm
SMYT 93x133		<p>Materials: Cordierite</p> <p>CO Discharged: <0.06</p> <p>Temperature softening: 1230°C</p> <p>Open Porosity: 61%</p> <p>Air consumption: 0.13kg/h</p> <p>Weight:</p>	W93mmxL133xH13mm
SHGT+ 100x140		<p>Materials: Cordierite</p> <p>CO Discharged: <0.06</p> <p>Temperature softening: 1230°C</p> <p>Open Porosity: 61%</p> <p>Air consumption: 0.13kg/h</p> <p>Weight:</p>	W100mmxL140xH13mm



บริษัท เอดีดี เฟอร์เนส จำกัด



ADD FURNACE CO.,LTD.

44 ซอยบรมราชชนนี 70 ถนนบรมราชชนนี แขวงศาลาธรรมสพน์ เขตทวีวัฒนา กรุงเทพฯ 10170

โทร: 02-888-3472 โทร: ออกแบบ:08-08-170-170 แฟกซ์: 02-888-3258

<https://www.add-furnace.com> E-mail: sales@add-furnace.com

Honeycomb Ceramic(Infrared Burner Plate)

SMYT 140x200		Materials: Cordierite CO Discharged: <0.06 Temperature softening: 1230°C Open Porosity: 61% Air consumption: 0.13kg/h Weight:	W140mmxL200xH13mm
RB8 100		Materials: Cordierite CO Discharged: Temperature softening: Open Porosity: Air consumption: Weight:	Φ 100mm
RG3 116		Materials: Cordierite CO Discharged: Temperature softening: Open Porosity: Air consumption: Weight:	Φ 116mm
RGX 129		Materials: CO Discharged: Temperature softening: Open Porosity: Air consumption: Weight:	Φ 129mm
RG8 135		Materials: CO Discharged: Temperature softening: Open Porosity: Air consumption: Weight:	Φ 135mm
RG8 150		Materials: CO Discharged: Temperature softening:	Φ 150mm
		Open Porosity: Air consumption: Weight:	



บริษัท เอดีดี เฟอร์เนส จำกัด




ADD FURNACE CO.,LTD.

44 ซอยบรมราชชนนี 70 ถนนบรมราชชนนี แขวงศาลาธรรมสพน์ เขตทวีวัฒนา กรุงเทพฯ 10170

โทร: 02-888-3472 โทร: ออกแบบ:08-08-170-170 แฟกซ์: 02-888-3258

<https://www.add-furnace.com> E-mail: sales@add-furnace.com

Honeycomb Ceramic(Infrared Burner Plate)

RGT 158		Materials: CO Discharged: Temperature softening: Open Porosity: Air consumption: Weight:	Φ 158mm
RSG3 162		Materials: CO Discharged: Temperature softening: Open Porosity: Air consumption: Weight:	Φ 162mm
RSG3 168		Materials: CO Discharged: Temperature softening: Open Porosity: Air consumption: Weight:	Φ 168mm